

⚠ CAUTION: INITIALLY THERE MAY BE AN ADVERSE IMPACT ON INDOOR AIR QUALITY IN THE GENERAL WORK AREA DURING INSTALLATION. Adequate ventilation of the work area should be maintained during the installation process without causing the entry of contaminants to other parts of the building. Persons who are sensitive to odors and/or chemicals should avoid the work area.

⚠ CAUTION: IRRITANT. Avoid eye and skin contact. If eye contact occurs, flush with water for 15 minutes and call physician. Use with positive fresh air cross-ventilation. Do not take internally. If swallowed, do not induce vomiting. Call physician immediately. Wash skin thoroughly after using. Close container after each use.
KEEP OUT OF REACH OF CHILDREN.

NOTE: Do not reuse container. Dispose of container and primer residue in accordance with federal, state and local waste disposal regulations. Do not flush primer down drains.

⚠ PRECAUCIÓN: INICIALMENTE, PUEDE HABER UN IMPACTO ADVERSO EN LA CALIDAD DEL AIRE INTERIOR EN EL ÁREA GENERAL DE TRABAJO DURANTE LA INSTALACIÓN. Durante el proceso de instalación, se debe mantener una ventilación adecuada del área de trabajo sin permitir que los contaminantes ingresen en otras partes del edificio. Las personas sensibles a los olores y/o a los productos químicos deben evitar el área de trabajo.

PRECAUCIÓN: IRRITANTE. PRECAUCIÓN: IRRITANTE. Evite el contacto con los ojos y la piel. Si el producto entra en contacto con los ojos, enjuáguelos con agua durante 15 minutos y llame a un médico. Utilice este producto con una ventilación cruzada de aire puro. No lo ingiera. Si se ingiere, no induzca al vómito. Llame a un médico inmediatamente. Lave bien la piel después del uso. Cierre el recipiente después de cada uso.
MANTÉNGALO ALEJADO DEL ALCANCE DE LOS NIÑOS.

NOTA: No utilice el recipiente nuevamente. Elimine el recipiente y el residuo de pintura base de acuerdo con las leyes federales, estatales y locales de eliminación de desechos. No arroje la pintura base en los desagües.

UPC

081833000290

FP00554036

01/07

HENRY®

Engineered with  technology

554 Floor Preparation & Repair

LevelPro™

Underlayment Primer

Prepares surfaces prior to self-leveling

- High-Strength
- Solvent-Free
- Excellent Coverage

Use with HENRY 555 LevelPro™ Self-leveling Underlayment to bond over concrete, concrete terrazzo, burnished concrete, wood subfloors, ceramic tile and cutback adhesive.

The Professional's
Formula for Success.™

Made in the USA

1 Quart (946 ml)

HENRY 554 LevelPro™ Primer is required as part of the HENRY 555™ LevelPro Self-leveling Installation System. HENRY 554 LevelPro Primer prepares the cleaned surface, improves the bond and helps prevent pinholes and bubbles in the finished underlayment surface.

SUBFLOOR PREPARATION (for a successful installation): All subfloors must be clean, sound, solid, completely dry and free of all contaminants.

INSTRUCTIONS:

FOR CONCRETE, CONCRETE TERRAZZO, or BURNISHED CONCRETE:

Terrazzo and burnished, steel-troweled or otherwise extremely smooth concrete with a glass-like finish must be mechanically roughened prior to priming. Shake well, and then mix HENRY 554 LevelPro Primer 1:1 with water. Apply with a soft bristle push broom. **DO NOT USE A PAINT ROLLER!** Cover the entire subfloor to receive underlayment. Do not leave any bare spots. Do not allow product to puddle. Allow primer to dry to a clear thin film (3 hrs. min., 24 hrs. max.). Extremely fast drying or low primer coverage may indicate highly absorbent or porous concrete. In this case, apply a first coat of primer diluted with 3 parts of water. Allow this coat to fully dry, then re-prime with a second coat of primer diluted 1:1 with water. Allow the second coat to dry completely (3 hrs. min., 24 hrs. max.) before leveling.

FOR WOOD SUBFLOORS: Sand wood to a clean, solid surface. Shake well, and then apply HENRY 554 LevelPro Primer at full strength to the clean wooden subfloor with a short napped paint roller. **DO NOT USE A PUSH BROOM! DO NOT DILUTE!** Cover the entire subfloor to receive underlayment. Do not leave any bare spots. Do not allow the primer to puddle. Allow primer to dry to a clear thin film (12 hrs. min., 24 hrs. max.).

FOR CUTBACK ADHESIVE: Wet scrape the adhesive to a thin, well-bonded residue that appears as nothing more than a transparent stain using the wet-scraping technique as recommended by the Resilient Floor Covering Institute (www.rfci.com). Shake well, and then apply HENRY 554 LevelPro Primer at full strength to the prepared residue with a soft bristle push broom. **DO NOT USE A PAINT ROLLER!** Cover the entire subfloor to receive underlayment. Do not leave any bare spots. Do not allow the primer to puddle. Allow primer to dry to a clear thin film (16 hrs. min., 24 hrs. max.).

FOR CERAMIC TILE: Ceramic tile must have glaze removed by mechanical means, such as grinding or similar methods. Resulting surface must be clean, well bonded and free of any wax or sealers. Shake well, and then apply HENRY 554 LevelPro Primer at full strength to the roughened ceramic tile with a soft bristle push broom. **DO NOT USE A PAINT ROLLER!** Cover the entire subfloor to receive underlayment. Do not leave any bare spots. Do not allow the primer to puddle. Allow primer to dry to a clear thin film (12 hrs. min., 24 hrs. max.). **DO NOT USE HENRY 554 LevelPro Primer TO PRIME NON-POROUS TILE SUCH AS PORCELAIN.** Contact the W.W. Henry Technical Department for more information.

Low substrate temperature and/or high ambient humidity will extend the drying time of the primer. Do not install Henry products until the primer has dried thoroughly.

NOTE: Non-porous substrates, such as porcelain tile, epoxy terrazzo or epoxy or urethane coatings, are not suitable to receive HENRY 554 LevelPro Primer.

DRYING TIME: Approx. 3 to 24 hrs.

COVERAGE: 100-150 sq. ft. per quart

SHELF LIFE: 1 year unopened

CLEAN UP: Clean tools with water while primer is still wet. Dispose of container and any unused contents in accordance with local regulations. **DO NOT POUR UNUSED MATERIAL INTO DRAIN.**

VOC content: 0 g/L (calculated)

For more information on installation, contact the Henry Technical Department at 800-232-4832, or refer to the W.W. Henry Web site.
© 2006 The W.W. Henry Company
www.wHenry.com